

TRIMITZCRYL FINISH 250
Acrylic Gloss Finish



Product Description	A fast drying, acrylic solvent based synthetic gloss enamel.																																	
Recommended Use	Finishing coat for protection of steel and concrete over suitable primer on interior and exterior areas.																																	
Characteristics	<ul style="list-style-type: none"> • Good gloss and colour retention. • Rapid drying-time. • Good exterior durability. • Good flexibility and abrasion resistance. 																																	
Physical Data	Colour	Available On Request																																
	Gloss Level	Gloss																																
	Volume Solid	Approx. 33%																																
	Dry Film Thickness	50 microns per coat																																
	Number of Coat	2																																
	Theoretical Coverage	6.60 sq.m/ltr for 50 microns																																
	Temperature Resistance	Maximum : 80°C (dry)																																
	VOC	441 g/ltr																																
	Flash Point	36°C																																
	Shelf Life	At least 12 months																																
	Pack Size	5 litres; 20 litres																																
Surface Preparation	Previous suitable primer coat, dry and free from any contamination.																																	
Application Data	<p>Application Methods</p> <table> <tr> <td>Airless Spray</td> <td></td> </tr> <tr> <td>Nozzle Tip</td><td>0.38 - 0.46 (0.015 - 0.018 inch)</td> </tr> <tr> <td>Nozzle Pressure</td><td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td>Conventional Spray</td> <td></td> </tr> <tr> <td>Nozzle Tip</td><td>1.8 - 2.0 mm (0.071 - 0.079 inch)</td> </tr> <tr> <td>Nozzle Pressure</td><td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td>Mixing Ratio</td><td>One component</td> </tr> <tr> <td>Thinner</td><td>Thinner Trimitz 910</td> </tr> <tr> <td>Cleaner</td><td>Thinner Trimitz 930</td> </tr> <tr> <td>Surface Temperature</td><td>Should be 10°C - 49°C, at least 3°C above the dew point to prevent condensation</td> </tr> <tr> <td>Drying Time</td><td></td> </tr> <tr> <td>Touch Dry</td><td>10 minutes at 25°C, 5 minutes at 32°C</td> </tr> <tr> <td>Trough Dry</td><td>2 hours at 25°C, 1 hour at 32°C</td> </tr> <tr> <td>Overcoating</td><td></td> </tr> <tr> <td>Minimum</td><td>2 hours at 25°C, 1 hour at 32°C</td> </tr> <tr> <td>Maximum</td><td>Unlimited (roughened and dry)</td> </tr> </table>		Airless Spray		Nozzle Tip	0.38 - 0.46 (0.015 - 0.018 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 - 2.0 mm (0.071 - 0.079 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Mixing Ratio	One component	Thinner	Thinner Trimitz 910	Cleaner	Thinner Trimitz 930	Surface Temperature	Should be 10°C - 49°C, at least 3°C above the dew point to prevent condensation	Drying Time		Touch Dry	10 minutes at 25°C, 5 minutes at 32°C	Trough Dry	2 hours at 25°C, 1 hour at 32°C	Overcoating		Minimum	2 hours at 25°C, 1 hour at 32°C	Maximum	Unlimited (roughened and dry)
Airless Spray																																		
Nozzle Tip	0.38 - 0.46 (0.015 - 0.018 inch)																																	
Nozzle Pressure	10 MPa (approx. 1400 psi)																																	
Conventional Spray																																		
Nozzle Tip	1.8 - 2.0 mm (0.071 - 0.079 inch)																																	
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																	
Mixing Ratio	One component																																	
Thinner	Thinner Trimitz 910																																	
Cleaner	Thinner Trimitz 930																																	
Surface Temperature	Should be 10°C - 49°C, at least 3°C above the dew point to prevent condensation																																	
Drying Time																																		
Touch Dry	10 minutes at 25°C, 5 minutes at 32°C																																	
Trough Dry	2 hours at 25°C, 1 hour at 32°C																																	
Overcoating																																		
Minimum	2 hours at 25°C, 1 hour at 32°C																																	
Maximum	Unlimited (roughened and dry)																																	

TRIMITZCRYL FINISH 250
Acrylic Gloss Finish

**System Compatibility****Primers**

- Trimitzpox MP 4850
- Trimitzpox Primer 471

For other suitable primers or intermediates, please consult Trimitz Protective Coating.

Safety Precaution

Keep away from heat, spark and open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.

Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

Disclaimer

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.