



TRIMITZFOX FLOOR T 101

Epoxy Polyamide Floor Coating Gloss Finish

Product Description	Two pack high solid epoxy polyamide gloss finish.																								
Recommended Use	A though cosmetic finishes for concrete in chemical, pharmaceutical and other industries.																								
Characteristics	<ul style="list-style-type: none"> • High gloss • Good abrasion resistance. • Excellent impact resistance. • Easy to clean. • Tough, smooth non porous surfaces. 																								
Physical Data	Colour	Available On Request																							
	Gloss Level	High Gloss																							
	Volume Solid	65%																							
	Dry Film Thickness	150 - 175 microns																							
	Number of Coat	1																							
	Theoretical Coverage	4.33 sq.m/ltr for 150 microns																							
	Mixing Ratio	Base : Hardener = 4 : 1																							
	Thinner	Thinner Trimitz 920																							
	Cleaner	Thinner Trimitz 920																							
	Pack Size	20 litres																							
	Shelf Life	12 months																							
	Pot Life	4 hours																							
	Temperature Resistance	93°C (dry)																							
	Flash Point	Base : 25°C Hardener : 48°C																							
	Drying Time																								
	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th rowspan="2">Substrate Temperature</th> <th rowspan="2">Touch dry</th> <th rowspan="2">Hard dry</th> <th colspan="2">To Top Coat</th> </tr> <tr> <th>Minimum</th> <th>Maximum</th> </tr> </thead> <tbody> <tr> <td>25 °C</td> <td>4 hours</td> <td>12 hours</td> <td>16 hours</td> <td>3 months</td> </tr> <tr> <td>32 °C</td> <td>2 hours</td> <td>12 hours</td> <td>12 hours</td> <td>3 months</td> </tr> <tr> <td>Full Cure</td> <td colspan="3" style="text-align: center;">7 days</td><td></td></tr> </tbody> </table>			Substrate Temperature	Touch dry	Hard dry	To Top Coat		Minimum	Maximum	25 °C	4 hours	12 hours	16 hours	3 months	32 °C	2 hours	12 hours	12 hours	3 months	Full Cure	7 days			
Substrate Temperature	Touch dry	Hard dry	To Top Coat																						
			Minimum	Maximum																					
25 °C	4 hours	12 hours	16 hours	3 months																					
32 °C	2 hours	12 hours	12 hours	3 months																					
Full Cure	7 days																								
Surface Preparation	<p>All surfaces to be coated should be clean, dry and free from contamination.</p> <p>Concrete</p> <p>Allow 28 days for concrete to cure. Remove surface laitance by acid etching, abrasive or scrapping, apply direct.</p>																								
Application Data	Application Methods	<p>Brush, Roller or Spray</p> <p>Recommended</p>																							

**TRIMITZFOX FLOOR T 101****Epoxy Polyamide Floor Coating Gloss Finish****Safety Precaution**

Keep away from heat, spark and open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.

Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

Disclaimer

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.