

## TRIMITZKYD PRIMER 240 ZP

## Alkyd Primer

<b>Product Description</b>	Anti corrosive zinc phosphate alkyd primer.																																			
<b>Recommended Use</b>	Economic general purposes maintenance and new building primer suitable for use on superstructures and on steel surfaces not normally exposed to water immersion.																																			
<b>Characteristics</b>	<ul style="list-style-type: none"> <li>• Fast dry alkyd primer.</li> <li>• To be recoated with conventional paint systems.</li> <li>• An economic primer for structural steel.</li> <li>• Pigmented with zinc phosphate, free of lead and chrome pigments.</li> </ul>																																			
<b>Physical Data</b>	Colour	White and Red																																		
	Gloss level	Flat																																		
	Volume Solid	Approx. 55%																																		
	Dry Film Thickness	50 microns per coat																																		
	Number of Coat	1																																		
	Theoretical Coverage	11.00 sq.m/ltr for 50 microns																																		
	Temperature Resistance	Continuous : 90°C Intermittent : 115°C																																		
	VOC	233 g/ltr																																		
	Flash Point	38°C																																		
	Shelf Life	At least 12 months																																		
	Pack Size	5 litres; 20 litres																																		
<b>Surface Preparation</b>	Dry abrasive blast to a minimum ISO - Sa 2 or SSPC - SP 6 "Commercial". Blast to achieve a 25 microns anchor profile as indicated with a Keane Tator Surface Profile Comparator. Remove abrasive residue or dust from surface.																																			
<b>Application Data</b>	<b>Application Methods</b> <table> <tr> <td>Airless Spray</td> <td></td> </tr> <tr> <td>Nozzle Tip</td><td>Approx. 0.28 mm (0.011 inch)</td> </tr> <tr> <td>Nozzle Pressure</td><td>10 MPa (approx. 1400 psi)</td> </tr> <tr> <td>Conventional Spray</td> <td></td> </tr> <tr> <td>Nozzle Tip</td><td>1.8 - 2.0 mm (0.071 - 0.079 inch)</td> </tr> <tr> <td>Nozzle Pressure</td><td>0.3 MPa (approx. 43 psi)</td> </tr> <tr> <td>Brush or Roller Recommended</td> <td></td> </tr> <tr> <td>Mixing Ratio</td><td>One component</td> </tr> <tr> <td>Thinner</td><td>Thinner Trimitz 900</td> </tr> <tr> <td>Cleaner</td><td>Thinner Trimitz 930</td> </tr> <tr> <td>Surface Temperature</td><td>Should be 10°C - 49°C, at least 3°C above the dew point to prevent condensation</td> </tr> <tr> <td>Drying Time</td> <td></td> </tr> <tr> <td>Touch Dry</td><td>30 minutes at 25°C, 15 minutes at 32°C</td> </tr> <tr> <td>Through Dry</td><td>2 hours at 25°C, 1 hour at 32°C</td> </tr> <tr> <td>To Topcoat</td> <td></td> </tr> <tr> <td>Minimum</td><td>12 hours at 25°C, 7 hours at 32°C</td> </tr> <tr> <td>Maximum</td><td>Unlimited (roughened and dry)</td> </tr> </table>		Airless Spray		Nozzle Tip	Approx. 0.28 mm (0.011 inch)	Nozzle Pressure	10 MPa (approx. 1400 psi)	Conventional Spray		Nozzle Tip	1.8 - 2.0 mm (0.071 - 0.079 inch)	Nozzle Pressure	0.3 MPa (approx. 43 psi)	Brush or Roller Recommended		Mixing Ratio	One component	Thinner	Thinner Trimitz 900	Cleaner	Thinner Trimitz 930	Surface Temperature	Should be 10°C - 49°C, at least 3°C above the dew point to prevent condensation	Drying Time		Touch Dry	30 minutes at 25°C, 15 minutes at 32°C	Through Dry	2 hours at 25°C, 1 hour at 32°C	To Topcoat		Minimum	12 hours at 25°C, 7 hours at 32°C	Maximum	Unlimited (roughened and dry)
Airless Spray																																				
Nozzle Tip	Approx. 0.28 mm (0.011 inch)																																			
Nozzle Pressure	10 MPa (approx. 1400 psi)																																			
Conventional Spray																																				
Nozzle Tip	1.8 - 2.0 mm (0.071 - 0.079 inch)																																			
Nozzle Pressure	0.3 MPa (approx. 43 psi)																																			
Brush or Roller Recommended																																				
Mixing Ratio	One component																																			
Thinner	Thinner Trimitz 900																																			
Cleaner	Thinner Trimitz 930																																			
Surface Temperature	Should be 10°C - 49°C, at least 3°C above the dew point to prevent condensation																																			
Drying Time																																				
Touch Dry	30 minutes at 25°C, 15 minutes at 32°C																																			
Through Dry	2 hours at 25°C, 1 hour at 32°C																																			
To Topcoat																																				
Minimum	12 hours at 25°C, 7 hours at 32°C																																			
Maximum	Unlimited (roughened and dry)																																			

## TRIMITZKYD PRIMER 240 ZP

## Alkyd Primer

**System Compatibility****Top Coat**

- Trimitzkyd Finish 250

For other suitable intermediates or topcoats, please consult Trimitz Protective Coating.

**Safety Precaution**

Keep away from heat, spark and open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.

Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

**Disclaimer**

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.